

Fugabella Color

Decorative Resina-cemento (resin-cement) for grouting of ceramic and porcelain tiles, mosaic and natural stone in a 50-colour design range. Green product for bio-building.

The groundbreaking hybrid grout Fugabella Color is ideal when decorating any surface in porcelain, ceramic tiles, mosaic and natural stone.

Fugabella Color achieves performance characteristics such as water-repellence, very low water absorption, high surface hardness, high resistance to the most common acidic substances and total colour uniformity.

1. Fine-grain finish
2. Superior flexibility
3. Water-repellent
4. High CATAS-tested chromatic uniformity
5. 50-colour collection, color designer Piero Lissoni
6. Easy to clean and maintain
7. Suitable for underfloor heating systems
8. Can be recycled as mineral inert material, avoiding waste disposal costs and environmental impact
9. Naturally antibacterial



Rating 4

- × Regional Mineral ≥ 60%
- ✓ Recycled Regional Mineral ≥ 30%
- ✓ CO₂ Emission ≤ 250 g/kg
- ✓ VOC Low Emission
- ✓ Recyclable

Rating based on average colour formulations

Areas of application

→ High-performance grouting of joints from 0 to 20 mm, with smooth finish, high degree of hardness and water-repellence.

Materials to be grouted:

- porcelain tiles, low thickness slabs, ceramic tiles, klinker, cotto, glass and ceramic mosaic, of all types and formats
- natural stone, recomposed materials, marble.

→ Intended use:

- internal and external flooring and walls, in domestic, commercial and industrial applications and street furniture, in environments subject to heavy traffic, also in

- areas subject to thermal shock and freezing
- swimming pools, tanks and fountains
- underfloor heating systems.

Do not use on joints more than 20 mm in width, on floors and walls where specific chemical resistances or absolutely no water absorption are required; to grout elastic expansion or fractionising joints; on substrates which are highly deformable, not perfectly dry or subject to moisture rising.

Instructions for use

→ Preparation of substrates

Before grouting joints, check that tiles have been laid correctly and are anchored perfectly to the substrate. Substrates must be perfectly dry. Grout joints in accordance with the recommended waiting time indicated on the relative data sheet for the adhesive used. For mortar substrates, wait at least 7 – 14 days depending on screed thickness, ambient weather conditions and on the level of absorption of the covering and the substrate. Any water or moisture rising can cause salt to build up on the surface of the grout or cause shade variations on account of the uneven evaporation of remaining water through the grout.

Joints must be free from any excess adhesive, even if already hardened, and must be of an even depth of at least $\frac{2}{3}$ of the overall thickness of the tile covering. This is necessary to prevent different drying times of each different thickness, with subsequent shade variations.

Any dust and loose debris must be removed from the joints by carefully cleaning them with a vacuum cleaner. In the case of highly absorbent tiles or high temperatures, a damp sponge should be passed across the surface of the tilework prior to grouting joints, in order to prevent any water from being left in the joints. Before grouting joints with contrasting colours, check the cleanability, as highly porous surfaces may make cleaning difficult. It is advisable to perform a preliminary test on tiles not to be laid or in a small, concealed area. In these cases we recommend treating the covering with specific protective products, being careful to avoid applying them to the joints.

→ Preparation

Prepare Fugabella Color in a clean container, first of all pouring in a quantity of water equal to approximately $\frac{3}{4}$ of the amount required. Gradually add Fugabella Color to the container, mixing with a suitable low-speed mixer (≈ 400 rpm). Add more water until the desired consistency is obtained. The mixture must be of smooth consistency and without any lumps. For best results, and to mix larger quantities of the grout, a stirring device with vertical blades and slow rotation is recommended. Specific polymers with high-dispersion properties ensure that Fugabella Color is immediately ready for use. Mix a quantity to be used within 60 min. at +23 °C 50% R.H. The amount of water to be added, indicated on the packaging, is an approximate guide and will vary depending on the different colours. It is possible to obtain mixtures with consistency of variable thixotropy according to the application to be made. Adding extra water does not improve the workability and the cleanability of the grout, and may cause shrinkage in the plastic phase of drying and result in less effective final performance. Prepare all mixtures required to complete the process using the same amount of water, in order to avoid any variations in grout shade.

→ Application

Fugabella Color must be applied evenly on the tile covering with a spreader or hard rubber float. Grout material has to be completely filled between entire joint areas, the application has to be done diagonally with respect to the joints. Remove most of the excess grout immediately, leaving only a thin film on the tile.

Instructions for use

→ Cleaning

Begin cleaning the tilework when the grout is touch dry into the joint. On completion, clean up the surface using a thick, large-sized sponge damped in clean water to avoid removing grout from the joints. Make sure clean water is used at all times, using appropriate trays with grills and cleaning rollers for the sponge.

Use circular movements to soften the film of

hardened grout on the tiles. Finish cleaning up by dragging the sponge diagonally across the tiles while applying water evenly over the tiles, in order to prevent any shade variations. Residual traces of grout can be removed from tools with water before the product has hardened.

Special notes

→ When using Fugabella Color to grout joints in large surface areas, use suitable electrical equipment to increase application speed and cleaning times. In particular, cleaning with electric sponges can be easily carried out and ensures superior coverage and perfect results in aesthetic terms.

→ Before grouting highly porous surface coverings, or at high temperatures, it is advisable to wipe a damp sponge over the surface to counteract the porosity or to cool the surface, being careful not to cause water to stagnate in the joints.

→ It is recommended to use materials from the same production batch throughout.

→ The partial or full replacement of mixing water with Fugaflex Eco eco-friendly flexibilizing latex for cement-based grouts, gives increased flexibility to Fugabella Color, reduces the elastic modulus, increases resistance to water and substrate adhesion. Its use is recommended in the following specific applications: laying on wooden floors, laying on substrates or using materials with high thermal expansion or where surfaces are to be subsequently smoothed.

→ Approved for marine use.

Certificates and marks



* Émission dans l'air intérieur Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

Abstract

*Certified, high-performance grouting of ceramic tiles, porcelain tiles, low thickness slabs, marble and natural stone with eco-friendly, naturally bacteriostatic and fungistatic mineral grout with high colour fastness, compliant with standard ISO 13007-3 - class CG2 WA, GreenBuilding Rating 3, such as Fugabella Color by Kerakoll Spa**. Joints must be dry and free from traces of adhesive and loose debris. Use a spreader or hard rubber float to apply the grout and suitable sponges and clean water to clean joints on completion. Joints of ___ mm width and tiles ___ x ___ cm in size will give an average coverage of approx. ___ kg/m². Existing elastic expansion and fractionizing joints must be respected.*

** Tests carried out according to CSTB method, bacterial and fungal contamination

Fugabella Color colour chart

Colour Fastness*
* GSc (Daylight)
EN ISO 105-A05
standard

01		4,5
02		4,5
03		4,5
04		4,5
05		4,5
06		4,5
07		4,5
08		4,5
09		5
10		4,5
11		5
12		5
13		4,5
14		4,5
15		4
16		4
17		4,5
18		4,5
19		4,5
20		5
21		4,5
22		4,5
23		4,5
24		4,5
25		4,5
26		4,5
27		5
28		5
29		4,5
30		4,5
31		4,5
32		4,5
33		4,5
34		4,5
35		4,5
36		4,5
37		4,5
38		4,5
39		4,5
40		4,5
41		4
42		3,5
43		5
44		4,5
45		5
46		4,5
47		5
48		4,5
49		4,5
50		4,5

The shades shown are intended as an indication only

Legend from 5 to 4 high colour fastness; for internal and external use
from 3,5 to 3 good colour fastness; for internal and external use
from 2,5 to 1 limited colour fastness; for internal use

* ageing data 500 hrs
Daylight.
ISO 11341:2004.
GSc (EN ISO 105 A05)

Technical Data compliant with Kerakoll Quality Standard		
Appearance	Coloured pre-mixed	
Apparent volumetric mass	≈ 1,22 kg/dm ³	UEAtc/CSTB 2435
Average granulometric composition	colour 01 ≈ 35 μm colours 02 – 50 ≈ 70 μm	
Mixing water:		
- 3 kg bag	≈ 0.7 l / 1 bag 3 kg	
- 20 kg bag	≈ 4.5 l / 1 bag 20 kg	
Shelf life:		
- 3 kg bag	≈ 24 months from production in the original sealed packaging, protect from humidity	
- 20 kg bag	≈ 12 months from production in the original sealed packaging, protect from humidity	
Pack	bags 20 kg – 3 kg	ISO 11600
Specific weight of the mixture	≈ 1.86 kg/dm ³	UNI 7121
Pot life:		
- ≈ +5 °C, 80% R.H.	≥ 120 min.	
- ≈ +23 °C, 50% R.H.	≥ 60 min.	
- ≈ +35 °C, 40% R.H.	≥ 30 min.	
Temperature range for application	from +5 °C to +35 °C	
Width of joints	from 0 to 20 mm	
Grouting after laying:		
- with adhesive	see characteristics of adhesive	
- mortar	≈ 7 – 14 days	
Foot traffic	≈ 3 hrs	
Foot traffic at +5 °C	≈ 10 hrs	
Foot traffic at +35 °C	≈ 2 hrs	
Interval before normal use	≈ 24 hrs	
Ready for use at +5 °C	≈ 3 days	
Ready for use at +35 °C	≈ 8 hrs	
Ready for use in swimming pools	≈ 3 days	
Coverage	see approximate Coverage table	

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site, i.e. temperature, ventilation and absorbency level of the substrate and of the materials laid.

Coverage table								
Format	Thickness	grammes/m ² joint width						
		1 mm	2 mm	3 mm	4 mm	5 mm	8 mm	12 mm
2x2 cm	3 mm	≈ 570	≈ 1140	≈ 1710	≈ 2280	≈ 2850	≈ 4560	≈ 6840
5x5 cm	4 mm	≈ 304	≈ 608	≈ 912	≈ 1216	≈ 1520	≈ 2432	≈ 3648
20x20 cm	8 mm	≈ 152	≈ 304	≈ 456	≈ 608	≈ 760	≈ 1216	≈ 1824
20x20 cm	14 mm	≈ 266	≈ 532	≈ 798	≈ 1064	≈ 1330	≈ 2128	≈ 3192
30x30 cm	10 mm	≈ 126	≈ 253	≈ 380	≈ 506	≈ 633	≈ 1013	≈ 1520
30x30 cm	14 mm	≈ 177	≈ 354	≈ 532	≈ 709	≈ 886	≈ 1418	≈ 2128
40x40 cm	10 mm	≈ 95	≈ 190	≈ 285	≈ 380	≈ 475	≈ 760	≈ 1140
50x50 cm	10 mm	≈ 76	≈ 152	≈ 228	≈ 304	≈ 380	≈ 608	≈ 912
30x60 cm	10 mm	≈ 95	≈ 190	≈ 285	≈ 380	≈ 475	≈ 760	≈ 1140
60x60 cm	10 mm	≈ 63	≈ 126	≈ 190	≈ 253	≈ 316	≈ 506	≈ 760
13.5x80 cm	10 mm	≈ 164	≈ 328	≈ 493	≈ 657	≈ 822	≈ 1315	≈ 1973
20x80 cm	10 mm	≈ 118	≈ 237	≈ 356	≈ 475	≈ 593	≈ 950	≈ 1425
40x80 cm	10 mm	≈ 71	≈ 142	≈ 213	≈ 285	≈ 356	≈ 570	≈ 855
80x80 cm	10 mm	≈ 47	≈ 95	≈ 142	≈ 190	≈ 237	≈ 380	≈ 570
11x90 cm	10 mm	≈ 193	≈ 387	≈ 581	≈ 775	≈ 969	≈ 1550	≈ 2326
22.5x90 cm	10 mm	≈ 105	≈ 211	≈ 316	≈ 422	≈ 527	≈ 844	≈ 1266
15x90 cm	10 mm	≈ 147	≈ 295	≈ 443	≈ 591	≈ 738	≈ 1182	≈ 1773
30x90 cm	10 mm	≈ 84	≈ 168	≈ 253	≈ 337	≈ 422	≈ 675	≈ 1013
60x90 cm	10 mm	≈ 52	≈ 105	≈ 158	≈ 211	≈ 263	≈ 422	≈ 633
50x100 cm	3 mm	≈ 17	≈ 34	≈ 51	≈ 68	≈ 85	≈ 136	≈ 205
100x100 cm	3 mm	≈ 11	≈ 22	≈ 34	≈ 45	≈ 57	≈ 91	≈ 136
10x120 cm	10 mm	≈ 205	≈ 411	≈ 617	≈ 823	≈ 1029	≈ 1646	≈ 2470
15x120 cm	10 mm	≈ 142	≈ 285	≈ 427	≈ 570	≈ 712	≈ 1140	≈ 1710
20x120 cm	10 mm	≈ 110	≈ 221	≈ 332	≈ 443	≈ 554	≈ 886	≈ 1330
30x120 cm	10 mm	≈ 79	≈ 158	≈ 237	≈ 316	≈ 395	≈ 633	≈ 950
60x120 cm	5 mm	≈ 23	≈ 47	≈ 71	≈ 95	≈ 118	≈ 190	≈ 285
120x120 cm	5 mm	≈ 15	≈ 31	≈ 47	≈ 63	≈ 79	≈ 126	≈ 190
100x300 cm	3 mm	≈ 7	≈ 15	≈ 22	≈ 30	≈ 38	≈ 60	≈ 91

The data provided must be considered merely as an indication of the grout coverage, averaged out based on our experience and taking into account normal site wastage. The following may vary according to specific conditions at the building site: roughness of tile, excess of residual product, lack of surface flatness, temperatures, seasonal conditions.

Performance		
VOC Indoor Air Quality (IAQ) - Volatile organic compound emissions		
Conformity	EC 1 Plus GEV-Emicode	GEV certified 9522/11.01.02
HIGH-TECH		
Flexural strength after 28 days	$\geq 2,5 \text{ N/mm}^2$	ISO 13007-4.1.3
Shrinkage	$\leq 3 \text{ mm/m}$	ISO 13007-4.3
Compressive strength after 28 days	$\geq 15 \text{ N/mm}^2$	ISO 13007-4.1.4
Resistance to frost-thaw cycles:		
- Flexural	$\geq 2,5 \text{ N/mm}^2$	ISO 13007-4.1.5
- Compressive	$\geq 15 \text{ N/mm}^2$	ISO 13007-4.1.5
Resistance to abrasion after 28 days	$\leq 1000 \text{ mm}^3$	ISO 13007-4.4
Water absorption after 30 min.	$\leq 2 \text{ g}$	ISO 13007-4.2
Water absorption after 240 min.	$\leq 5 \text{ g}$	ISO 13007-4.2
Colour Fastness	see colour chart	UNI EN ISO 105-A05
Fungal contamination	Resistant	CSTB SB-2018-144
Bacterial contamination	class B+	CSTB SB-2018-142
Working range	from $-40 \text{ }^\circ\text{C}$ to $+90 \text{ }^\circ\text{C}$	
Conformity	CG2 WA	ISO 13007-3

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

Warning

- Product for professional use
- abide by any standards and national regulations
- in swimming pools, check the suitability of the product based on the type of water and the type of chemical or physical treatment used
- grout shades are not reproducible and may even vary during application, as a result of application techniques and ambient conditions during and immediately after the grout has been applied
- workability times may vary considerably, depending on environmental conditions and on tile and substrate absorbency
- protect the grout from direct rainfall and sun for at least 12 hours after application
- in warm climates cool the surface and mix the grout with cold water
- grouting joints on substrates that are still damp will cause variations in the grout
- width of the joints: abide by any national regulations for the minimum sizing
- if necessary, ask for the safety data sheet
- for any other issues, contact the Kerakoll Worldwide Global Service +39 0536 811 516 - globalservice@kerakoll.com

Kerakoll Quality System ISO 9001 CERTIFIED 1710/0327	Kerakoll Quality System ISO 14001 CERTIFIED 18586-E	Kerakoll Quality System ISO 45001 CERTIFIED 18586-I
--	---	---

The Rating classifications refer to the GreenBuilding Rating Manual 2013. This information was last updated in January 2023 (ref. GBR Data Report – 02.23); please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions in your building yards and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.